



Productspecification/Information

EDEL-ELITE SUPERSOFT

A	Name of product Sports application	EDEL-ELITE SUPERSOFT Tennis, Multipurpose
B	Producer Production process	EDEL GRASS B.V. - Genemuiden - The Netherlands tufted, cut pile
C	Pile material Yarn Dtex Cross-section of tapes Colour Line colour UV-stability Light fastness Colour fastness	Thiolon® TS LSR polyethylene yarn, fibrillated, knit-d-knit thermofixated micro-curl, environment friendly, UV-stabilised 7300/1 Dtex width : approx. 12.7 mm thickness : approx. 63 µm olive green/summer green/red clay white/yellow/reflex blue/fire red DIN 53387 meets 6000 hours W.O.M. test >7 on blue scale 1-8 >4 on gray scale 1-5
D	Primary backing Coating Water permeability	Thiobac® polypropylene, UV-stabilised, appr. 135 gr/m ² Carboxylated (SBR) latex, appr. 1064 gr/m ² with 4mm perforation holes 60 liter/min/m ²
E	Product details Pile height Total construction height Pile weight Total weight Gauge Stitch per m ¹ linear Stitch per m ²	 appr. 10 mm (stretched) ±10% appr. 10 mm ±10% appr. 1220 gr/m ² ±10% appr. 2419 gr/m ² ±10% 3/16" 300 ±10 appr. 63000 ±10%
F	Infill Stabilizing infill Amount	silica-sand, gradation 0.25 - 0.7 mm, min. 80% round of shape appr. 12 kg/m ²
G	Installation method Roll width Roll length Joints/seams Line marking	loose laid on bound or unbound sub-base 3.72 m ¹ (± 2 cm) - tenniskit-system according to installation schedule the seams in the turf are joined with a reinforcing tape glued to the back of the turf tufted-in or to be laid in by installation
H	Approvals	ITF (CS 01/02-10-062)

The above data are subject to modifications based on technical improvements or company-internal developments. All data are higher than the DIN-standards. All figures are average values and can vary slightly.